

### General Information

#### Description

SEETEC VA900 resin is produced by ExxonMobil Chemical's autoclave process technology. SEETEC VA900 resin, with 28% VA content, is an excellent raw material in the application of hot melt adhesives.

#### Additives

- Antioxidant
- Free flow agent

#### Applications

- Hot melt adhesives

### Physical Properties<sup>1</sup>

Properties	Nominal Value	Unit	Test Method
Melt Index	150.0	g/10min	ASTM D1238
Vinyl Acetate	28	wt. %	LC Method
Density	0.950	g/cm <sup>3</sup>	ASTM D1505
Melting Point	67	°C	LC Method
Hardness	21	D scale	ASTM D2240
Vicat Softening Point	< 40	°C	ASTM D1525

#### NOTE

ISO 9001, 14001, ITS 10940

<sup>1</sup> Physical Properties : these are not to be construed as specifications