

LUCENE™ SP988

Metallocene Polyethylene

Applications

- Hot & cold drinking water pipe, Floor heating, Radiator connection, Al composite pipe

Description

- LUCENE™ SP988, LG PE-RT(TypeII) is a high performance MDPE for hot and cold water pipe. It is developed by using a new LG catalyst technology.
- It has excellent stress crack resistance properties and Long Term Hydrostatic strength.
- LUCENE™ SP988 Polyethylene Resin meets requirements of the FDA regulation 177.1520 and NSF/ANSI Standard 61 (Drinking Water System Components - Health Effect).

Typical properties

Characteristics	Test Method	Unit	Value
Physical⁽¹⁾			
MFR(190°C,2.16Kg)	ASTM D1238	g/10min	0.6
Density	ASTM D1505	g/cm³	0.941
Mechanical⁽²⁾			
Tensile Strength at Yield	ASTM D638	MPa	20
Tensile Strength at Break	ASTM D638	MPa	37
Elongation at Break	ASTM D638	%	750
Hardness (Rockwell)	ISO 868	R Scale	57
Flexural Modulus	ISO178	MPa	660
Izod Impact Strength	ASTM D256	J/m	Non Break
ESCR(F50)	ASTM D1693	hr	> 8,760
Thermal			
Melting Temperature	LG Method	°C	128
Vicat Softening Point	ASTM D1525	°C	125

(1) The properties data in this table are typical values, and not guaranteed specification.

(2) Typical resin property values are measured on a standard compression molded specimens

For additional sales, order and technical assistance

Head office PO Division, LG Chem Ltd.

Yeoui-do P.O.Box 672, 21st floor LG Twin Tower,
Yeoui-daero 128, Yeongdeungpo-gu Seoul, Korea.
Tel. 82-2-3773-3063

TS&D

TECH Center. Polyolefin

175, Gajeong-ro, Yuseong-gu, Daejeon, 305-343, Korea.
Tel. 82-42-860-8239

Revised :02/03/2016

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. LG Chem makes no warranty or guarantee, expressed or implied, (i) that the result described herein will be obtained under end - use conditions, or (ii) as to the effectiveness or safety of any design incorporating LG Chem materials, products, recommendations or advice. Further, any information contained herein shall not be construed as a part of legally binding offer. Especially, the typical values should be regarded as reference values only and not as binding minimum values. Each user bear full responsibility for making its own determination as to the suitability of LG Chem's materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating LG Chem material or products will be safe and suitable for use under end - use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products."

LUCENE™ SP988

Metallocene Polyethylene

Processing information

- Equipment : Single Screw Extruder(Conventional PE Screw)
- Temperature :

Hopper zone	Cylinder (Barrel)	Head / Die zone
cooled	180 ~ 230°C	220 ~ 230°C

- Die to Calibration : 2 ~ 10cm
- Recommendation : Screw C/R ; 2.2 ~ 2.5
Screw L/D ; 24 ~ 30
Die Gap ; Wall Thickness X 1.7 ~ 2.5
- The actual extrusion conditions depend on the screw, die design, pipe diameter, wall thickness and throughput rate.

For additional sales, order and technical assistance

Revised :02/03/2016

Head office PO Division, LG Chem Ltd.
Yeoui-do P.O.Box 672, 21st floor LG Twin Tower,
Yeoui-daero 128, Yeongdeungpo-gu Seoul, Korea.
Tel. 82-2-3773-3063

TS&D TECH Center. Polyolefin
175, Gajeong-ro, Yuseong-gu, Daejeon, 305-343, Korea.
Tel. 82-42-860-8239

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. LG Chem makes no warranty or guarantee, expressed or implied, (i) that the result described herein will be obtained under end - use conditions, or (ii) as to the effectiveness or safety of any design incorporating LG Chem materials, products, recommendations or advice. Further, any information contained herein shall not be construed as a part of legally binding offer. Especially, the typical values should be regarded as reference values only and not as binding minimum values. Each user bear full responsibility for making its own determination as to the suitability of LG Chem's materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating LG Chem material or products will be safe and suitable for use under end - use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products."