

# CAMPUS® Datasheet

Makrolon® 2607 - PC

Covestro Deutschland AG



## Product Texts


- MVR (300 °C/1.2 kg) 12 cm<sup>3</sup>/10 min
- general purpose
- medium viscosity
- UV stabilized
- easy release
- available in transparent, translucent and opaque colors

Rheological properties	Value	Unit	Test Standard
Melt volume-flow rate, MVR	12	cm <sup>3</sup> /10min	ISO 1133
Temperature	300	°C	ISO 1133
Load	1.2	kg	ISO 1133
Molding shrinkage, parallel	0.7	%	ISO 294-4, 2577
Molding shrinkage, normal	0.8	%	ISO 294-4, 2577
Mechanical properties	Value	Unit	Test Standard
Tensile Modulus	2400	MPa	ISO 527-1/-2
Yield stress	66	MPa	ISO 527-1/-2
Yield strain	6.1	%	ISO 527-1/-2
Nominal strain at break	>50	%	ISO 527-1/-2
Tensile creep modulus, 1h	2200	MPa	ISO 899-1
Tensile creep modulus, 1000h	1900	MPa	ISO 899-1
Charpy impact strength, +23°C	N	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength, -30°C	N	kJ/m <sup>2</sup>	ISO 179/1eU
Puncture - maximum force, +23°C	5400	N	ISO 6603-2
Puncture - maximum force, -30°C	6300	N	ISO 6603-2
Puncture energy, +23°C	60	J	ISO 6603-2
Puncture energy, -30°C	65	J	ISO 6603-2
Thermal properties	Value	Unit	Test Standard
Glass transition temperature, 10°C/min	143	°C	ISO 11357-1/-2
Temp. of deflection under load, 1.80 MPa	123	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	135	°C	ISO 75-1/-2
Vicat softening temperature, 50°C/h 50N	143	°C	ISO 306
Coeff. of linear therm. expansion, parallel	65	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	65	E-6/K	ISO 11359-1/-2
Yellow Card available	Yes	-	-
Burning Behav. at thickness h	V-2	class	IEC 60695-11-10
Thickness tested (h)	0.8	mm	IEC 60695-11-10
Oxygen index	28	%	ISO 4589-1/-2
Electrical properties	Value	Unit	Test Standard
Relative permittivity, 100Hz	3.1	-	IEC 60250
Relative permittivity, 1MHz	3	-	IEC 60250
Dissipation factor, 100Hz	5	E-4	IEC 60250
Dissipation factor, 1MHz	90	E-4	IEC 60250
Volume resistivity	>1E13	Ohm*m	IEC 60093
Surface resistivity	>1E15	Ohm	IEC 60093
Electric strength	34	kV/mm	IEC 60243-1


Comparative tracking index	250	-	IEC 60112
<b>Other properties</b>			
Water absorption	0.3	%	Sim. to ISO 62
Humidity absorption	0.12	%	Sim. to ISO 62
Density	1200	kg/m <sup>3</sup>	ISO 1183
<b>Material specific properties</b>			
Luminous transmittance	89	%	ISO 13468-1, -2
<b>Rheological calculation properties</b>			
Density of melt	1020	kg/m <sup>3</sup>	-
Thermal conductivity of melt	0.214	W/(m K)	-
Spec. heat capacity melt	2100	J/(kg K)	-
Eff. thermal diffusivity	1E-7	m <sup>2</sup> /s	-
Ejection temperature	130	°C	-
<b>Test specimen production</b>			
Injection Molding, melt temperature	290	°C	ISO 294
Injection Molding, mold temperature	80	°C	ISO 10724
Injection Molding, injection velocity	200	mm/s	ISO 294

#### Diagrams


##### Viscosity-shear rate




##### Shearstress-shear rate




Dynamic Shear modulus-temperature




Stress-strain




Secant modulus-strain




Stress-strain (isochronous) 23 °C




Creep modulus-time 23 °C




Stress-strain (Isochronous) 40 °C




Creep modulus-time 40 °C




Stress-strain (Isochronous) 60 °C




Creep modulus-time 60°C




Stress-strain (isochronous) 90°C




Creep modulus-time 90°C




Stress-strain (isochronous) 120°C



Creep modulus-time 120 °C



Specific volume-temperature (pvT)



Characteristics

Processing

Injection Molding

Delivery form

Pellets

Additives

Release agent

Special Characteristics

Light stabilized or stable to light, U.V. stabilized or stable to weather, Transparent

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Other text information

Injection molding

PREPROCESSING

Max. Water content: 0.01 - 0.02 %

Drying temperature: 120 °C

Drying time:

Circulating air drying oven (50 % fresh air) 4-8 h

Fresh air dryer (high speed dryer) 2-4 h

Dry air dryer 2-3 h

PROCESSING

Melt temperature: 280-320 °C

Mold temperature: 80-100 °C

Use open nozzle.

Typical value

These values are typical values only. Unless explicitly agreed in written form, they do not constitute a binding material specification or warranted values. Values may be affected by the design of the mold/die, the processing conditions and coloring/pigmentation of the product. Unless specified to the contrary, the property values given have been established on standardized test specimens at room temperature.

General

The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance, information and recommendations to determine to your own satisfaction whether our products, technical assistance and information are suitable for your intended uses and applications. This

application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by Covestro.

Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale which are available upon request. All information and technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with any claim of any patent relative to any material or its use. No license is implied or in fact granted under the claims of any patent.

#### Medical Grades

Only Covestro products that are designated as "Medical Grade" may be used in medical devices or intermediates of medical devices. The designation as "Medical Grade" does not mean that Covestro or anyone else has determined that the product is suitable for use in any particular Medical Application. Except when Covestro has expressly agreed in writing to the sale of these products for such applications, Covestro products designated as "Medical Grade" shall not be considered candidates for any Medical Applications in: (a) cosmetic, reconstructive or reproductive implants, (b) other body implants, (c) applications involving contact with or storage of human tissue, blood or other bodily fluids for longer than 30 days, or (d) applications involving contact for longer than 24 hours with circulating blood, tissue, bone or dentin.

For further information on the use of Covestro products in Medical Applications, please request from your sales support contact our Guidance document: GUIDANCE ON USE OF COVESTRO PRODUCTS IN A MEDICAL APPLICATION.

[plastics.covestro.com](http://plastics.covestro.com)