



ISO 9001:2000  
Certificate No.: CH98/8032

ISO 14001:2004  
Certificate No.: CH03/0112

OHSA 18001:1999  
Certificate No.: CH05/0675

**Address:**

No. 3, Taban St.,  
Valie-e-Asr St.,  
Tehran - Iran

**Tel:**

(+98 21)82122700

**Fax:**

(+98 21)8867 4126-27

**Web-site:**

[www.rpc-ir.net](http://www.rpc-ir.net)

**E-mail:**

[Sales@rpc-ir.net](mailto:Sales@rpc-ir.net)

## High Density Polyethylene

### EX3

Typical properties	Test method (DIN)	Unit	Value
MFI@190°C, 5Kg	53735	gr/10min	0.50
Density	53479	gr/cm <sup>3</sup>	0.944
Impact Strength(Charpy Index)	53453	mj/mm <sup>2</sup>	22
Resistance to internal pressure (80°C,4N/mm <sup>2</sup> )	8074	hr	≥170

➤ Values shown are averages & are not to be considered as product specifications.

#### ❖ Main application & Characteristics:

EX3 is high molecular weight, high density polyethylene copolymers, developed as general purpose resin for use in pressure and non-pressure pipes. A minimum service life of 50 years is achievable under appropriate pressure and temperature conditions. EX3 offer excellent chemical resistance and environmental stress crack resistance.

EX3 is suitable for extrusion into a full range of pipe and fittings sizes, where high density resins are required.

EX3 is suitable for use in transport of a wide range of fluids for industrial, rural and mining applications.

Suitability for use in any application should be determined by appropriate performance testing.

\* EX3 is suitable for food contact.