



RAVATHANE®

Technical Data Sheet

Ravathane® 130 A95

Description: Thermoplastic polyurethane elastomer based on polyester having strong resilience and tear resistance, excellent abrasion resistance, higher resistance to hydrolysis failure and oxidation, good stability towards solvents and light.

Application: Injection molding.

Typical Properties

PROPERTIES	TEST METHOD	UNITS	VALUES
Hardness	ISO 868	Shore A	95
Density	ISO 1183-1 A	g/cm ³	1,22
Tensile stress at:			
-100% elongation	ISO 37	MPa	9,5
-300% elongation	ISO 37	MPa	19
Tensile strength at break	ISO 37	MPa	40
Elongation at break	ISO 37	%	570
Tear strength	ISO 34-1 B/b	N/mm	165
Abrasion resistance	ISO 4649	mm ³	40

Properties have been tested on injection molded plaques conditioned 24 hours at room temperature before testing.

Application Guideline (Injection Molding)

Nozzle (°C)	Metering (°C)	Compression (°C)	Feed (°C)
210-220	205-215	200-210	195-205

Before processing, the pellets have to be dried at 80-90°C for 2-4 hours. Maximum moisture content should be below 0.02%.

Disclaimer: The information provided here is for reference only. We request that customers test our products in their application. We guarantee that our products will meet our written specifications. The customers are welcome to contact our customer and our technical service department in case of question about our products.



Supplier: RAVAGO PETROKİMYA SATIŞ VE PAZARLAMA A.Ş., TATLISU MH. ARIF AY SK. NO: 10 ŞERİFALİ - ÖMRANIYE - İSTANBUL

TEL: 0850 314 79 99 / FAX: 0282 868 00 08
Zip Code: 34774 Website: www.ravagopetrokimya.com